

M.Kaindl Holzindustrie
 Kaindlstraße 2
 A-5071 Wals / Salzburg

Telephone 0662 / 8588
 Fax 0662 / 8588 2034
 Email: holzeinkauf@kaindl.com



KAINDL

Quality and dimension specifications for Saw dust (SD), shavings (SV), chip pins (CP)

(July 2000)

Dimensions	Type	Standard quality	Rejects
Dimensions (width or thickness)		80% between: <6mm & >0.63 mm max. 10% > 6mm max. collateral Length: 15 mm	> 10% > 6mm
Ratio of cubic chippings to flat chippings	SD SV CP	Ratio 40 : 60 Ratio 30 : 70 Ratio 60 : 40	> 40% cubic > 30% cubic > 60% cubic
Dust ratio: (< 0,4 mm)	SD PV CP	max. 10% max. 10% max. 5%	> 10% > 10% > 5%
Quality:		Made from fresh wood, no red striping, no or little blueing.	More than 50% of Sawdust with red striping, rotting chips, more than 50% of chips with
Bark proportion:		max. 5% permissible	over 5% bark ratio.
<p>Sawdust made from old wood are excluded, as are impurities such as nails, stones, snow, lumps of ice and other foreign particles. The supplier will be held liable pursuant to the Product Liability Act for any consequential damage (e.g. cutter spindle, blade sets, etc.)</p>			