



Quality and dimension specifications for slabwood

(July 2000)

Dimensions Quality	Standard quality	Secondary quality	Rejects
Length	3 to 6 m long		< 3 m > 6 m long
minimum diam.:	50 cm / bundle	30 – 50 cm / bundle	< 30 cm / bundle > 100 cm / bundle
Max. diam.:	80 cm / bundle	> 80 – 100 cm / bundle	
Ties:	Steel, tied 4x	Plastic, tied 2 – 3 x or 6 x and more	Tied 1x, untied, loosely tied so that proper handling is not possible
Quality:	<p>Fresh slabs full suitability for storage</p> <p>Splinters and slabs mixed as occurring naturally</p> <p>The inclusion of saw wool and bark is impermissible</p>	<p>Splinters from long-term storage with limited suitability for storage</p> <p>Splinters with no inclusion of slab wood</p>	<p>Previous long-term storage renders very low or no suitability for storage</p> <p>The inclusion of saw wool in bundles will cause the entire bundle to be classified as reject material. We retain the right to classify entire loads as reject material if bark is included in the bundle.</p>
	<p>Slabs from recycling wood is excluded, as are nails, stones and other foreign bodies.</p> <p>The supplier will be held liable pursuant to the Product Liability Act for any consequential damage (e.g. cutter spindle, blade sets, etc.)</p>		