

AQUapro Supr. ET 8.0 PP

Productdescription: Laminate Flooring digitally printed

K 271

Stand: 01.21




System




- 1 Multi-layer UV coating
- 2 digital printed surface
- 3 HDF Optima
- 4 UV-coating

Profile



4-side micro bevel -35° / $-0,6\text{mm}$ wide

Kaindl Loc
profile longitudinal



Kaindl Tap Loc
profile transversal

| Tests | Flooring1 Symbols | Results |
|--|-----------------------------------|--|
| Panel dimension | | 1383x159x8mm |
| Service category per Standard per | EN ISO 10874 EN 15468:2016 | 32 |
| Abrasion resistance | EN 15468 :2016 Annex A | AC4 |
| Impact resistance small ball Impact resistance big ball | EN 15468:2016 | $\geq 12\text{N}$ $\geq 750\text{mm}$ |
| Formaldehyde emission of the substrate before coating | EN 120 DIBT-Richtlinie 100 | E1 |
| Formaldehyde emission | EN 717-1 | < 0,1 ppm |
| | EN 717-2 | < 3,5 mg/h m ² |

All values are approximate values - fluctuations cannot be absolutely ruled out.

| | | | |
|---|------------------------------|--|---|
| Micro-scratching resistance | EN 15468:2016 | | ≤ 2 |
| Moisture residue HDF | EN 322 | | 4 - 7% |
| Thickness swelling | EN 15468:2016 | | $\leq 18\%$ |
| Thermal conductivity | ISO 8302 | | 0,0780 m ² .K/W |
| Light fastness | EN 20105-B02 EN 20105 A02 | | not worse than 6 Blue wool scale not worse than 4 Grey scale |
| Lifting resistance | EN 13329 | | $\geq 1,25 \text{ N/mm}^2$ |
| Resistance to stains | EN 438-2.15 | | groups 1-2 grade 5 group 3 grade 4 |
| Combustibility | EN 13501-1 | | Cfl , s1 |
| Adhesion of the lacquer | EN 13893 | | \leq class 2 |
| Sliding friction μ | EN 13893 | | > 0,3 |
| Dimensional variants after changes in relative humidity | EN 13329 | | length and width $\leq 0,9 \text{ mm}$ |
| Straightness of the panels | EN 13329 | | $\leq 0,30 \text{ mm/m}$ |
| Hight difference between elements | EN 13329 | | max $\leq 0,15 \text{ mm}$ $\varnothing \leq 0,1 \text{ mm}$ |
| Squared elements | EN 13329 | | $\leq 0,20 \text{ mm}$ |
| Flatness of the element width | EN 13329 | | konkav $\leq 0,17 \text{ mm}$ konvex $\leq 0,23 \text{ mm}$ |
| Flatness of the element length | EN 13329 | | konkav $\leq 6,9 \text{ mm}$ konvex $\leq 13,8 \text{ mm}$ |
| System pattern matching widthwise | EN 13329 | | $\pm 2 \text{ mm}$ |

1)Information under www.floorsymbols.com