KAINDL Decor Chipboard P2 E1/CA

Technical Data Sheet


DSP2E1 01/20-03

Areas of use / Application

Numerous applications for non load-bearing purposes in dry areas for interior decoration

Construction

decorative paper chipboard P2 E1/CA decorative paper



Standard size

standard size: 2800 x 2070 mm thickness range: 8 - 38 mm

Properties

	classification acc. to EN 312	test method
formaldehyde release:	E1	EN 16516 1)
	Requirements fulfilled	CARB / EPA
	Requirements fulfilled	TSCA Title 2)
board moisture content at despatch:	5 - 13 %	EN 322
pentachlorophenol:	< 0,5 ppm	
bonding:	free of chloride	
wood species:	mainly conifers, oak/beech < 5%	
manufacturing process:	System ContiRoll	

¹⁾ Determination according to German Chemikalienverbotsverordnung according to procedure published in Bundesanzeiger on 26.11.2018; Annex 1. Valid as of 1.1.2020.

Tolerances

	unit		test method		
thickness tolerance		< 15	≥ 15 - 20	> 20	EN 14323
relating to the basic thickness:	mm	+/- 0,3 for abrasion class 1 und 2			
		+ 0,5/- 0,3 for abrasion class 3A, 3B +/- 0,5 and 4 according table 2			
length, and width telegrape.					
length- and width tolerance:					EN 44000
- standard size	mm	+/- 5			EN 14323
- cut sizes	mm	+/- 2,5			
			≤ 2		
distortion:	mm/m	(only for balanced assembling of the surface)			EN 14323
edge disruption:					
	mm/m		< 10		EN 14323
- standard size	mm/m	≤ 10 ≤ 3			EN 14323
- cut sizes	mm/m				

²⁾ Meets testing and monitoring requirements acc. to Airborne Toxic Control Measure (ATCM) to Reduce Formaldehyde Emission from Composite Wood Products -§ 93120 - 93120.12, title 17, California Code of Regulations - by the California Air Resources Board (CARB), as well as US EPA TSCA Title VI - 40

Average values

		classification acc. to EN 312					
		Thicknesses <mm></mm>					
	unit	<6to13	<13to20	<20to25	<25to32	<32to40	test method
density:	kg/m3	at factory specification					
bending strength:	N/mm²	11	11	10,5	9,5	8,5	EN 310
bending elasticity module:	N/mm²	1800	1600	1500	1350	1200	EN 310
cross tensile strength:	N/mm²	0,4	0,35	0,3	0,25	0,2	EN 319
surface soundness:	N/mm²	0,8	0,8	0,8	0,8	0,8	EN 311

Surface properties

unit	classification acc	test method	
N	≥ 1,5	EN 14323	
mm²/m² mm/m²	•	EN 14323 EN 14323	
group	≥ 3	EN 14323	
group	≥ 3	EN 14323	
grade	4 = moderate change of gl	EN 14323	
group		EN 14323	
class IP rotations WR rotations	Print Decor: Wood, Fantasy and Metallic 1 < 50 <150	Uni Decor 3A >150	EN 14323
	N mm²/m² mm/m² group group grade group class IP rotations WR	N ≥ 1,5 mm²/m² punctiform imperente group ≥ 3 group ≥ 3 grade 4 = moderate change of gl group > 6 Print Decor: Wood, Fantasy and Metallic Class IP rotations WR VR	N ≥ 1,5 mm²/m² punctiform imperfection < 2

Reaction to fire classification

decor chipboard	substrate chipboard	thickness	classification acc. to EG decision (2007/348/EG)*		
			end use condition	class	
KAINDL Decor Chipboard P2 E1/CA	density ≥ 600kg/m³	≥ 9 mm	without an air gap between the wood-based panel	D-s2, d0	
		≥ 9mm	with a closed or a open air gap not more than 22mm behind the wood-based panel	D-s2, d2	
		≥ 15mm	with a closed air gap behind the wood based panel	D-s2, d0	
		≥ 18mm	with an open air gap behind the wood based panel	D-s2, d0	
		≥ 3mm	any	E	
further information can be found in the Official Journal of the European Union and the Kaindl Info Sheet No. 9					

Storage tips

Kaindl Decor Chipboards P2 E1/CA should always be stored flat and level. The air temperature in storage room should be at 18-22°C, the relative air humidity at 50 to 60%. See also Standard CEN/TS 12872:2006

Cleaning and care

Kaindl Decor Chipboards P2 E1/CA are very hygienic and easy to clean.

All domestic cleaning agents can be used for cleaning Kaindl Decor Chipboards P2 E1/CA.Do not use scouring agents.

For daily care it is only necessary to clean Kaindl Decor Chipboards P2 E1/CA with a damp cloth. Handle in the same way as conventional wooden boards. Sanding, sealing or polishing the surface is not necessary because of the special surface.

Stubborn stains such as paint, adhesive, nail polish or oil can be cleaned off with acetone, vinegar concentrate, nail polish remover and universal thinner. In either case please use those agents sparingly, carefully and only in polluted areas.

Those agents must not stay on the surface for any length of time.

Cutting with knives directly on Kaindl Decor Chipboards P2 E1/CA will lead to scratches on the surface.

Always use a kind of underlay or protective mat.

Wipe off moisture around seams.

. When using any kind of computer mouse - a mouse mat must always be used!

Further processing

Kaindl Decor Chipboards P2 E1/CA can be processed by common wood working machines.

Before processing Kaindl Decor Chipboards P2 E1/CA please inspect for any visible damages.

To receive a proper cut quality various measures like e.g. feed rate, pitch and geometry of the saw tooth, chip room of the saw blade, excess of the saw blade etc.

If you have any further questions please connect your salesperson or see www.kaindl.com

The recommendations and information given in this Product Sheet are to the best of our knowledge in keeping with the present state of the art.

However, they are intended purely for information purposes and as noncommittal quide-lines. As such they cannot constitute grounds for any claim under warranty.