

CLASSIC T. 7.0 Standard Plank

Product description

P G51

Stand: 12.17



System



- 1 high-grade durable overlay
- 2 impregnated decorative paper
- 3 HDF low swelling
- 4 balancer

Profile



Kaindl Loc
on long and short side

Tests	Flooring ¹ Symbols	Results
Panel dimension		1383x193x7mm
Service category per Standard per	EN 685 EN 13329 	31
Abrasion resistance	EN 13329 	AC3
Impact resistance small ball big ball	EN 13329 	≥8N ≥500mm
Formaldehyde emission of the substrate before coating	EN 120 DIBT- Richtlinie 100 	E1 [Europe]
Formaldehyde emission	EN 717-1	< 0,1 ppm
	EN 717-2	< 3,5 mg/h m ²

All values are approximate values - fluctuations cannot be absolutely ruled out.

Floorconstruction		GREENGUARD
Formaldehyde emission	CARB	CARB Phase 2
Thickness swelling / edge swelling	EN 13329	< 18 %
Thermal conductivity	ISO 8302	0,0690 m ² .K/W
Moisture residue HDF	EN 322	4 - 7 %
Resistance to cigarette burns	EN 438-2.18	grade 4
Light fastness	EN ISO 105-B02 EN 20105-A02	not worse than 6 Blue wool scale not worse than 4 Grey scale
Lifting resistance	EN 13329	≥ 1 N/mm ²
Cross tensile strength	EN 319	> 1 N/mm ²
Resistance to stains	EN 438-2.15	groups 1-2 grade 5 group 3 grade 4
Combustibility	EN13501-1	Cfl , s1
Sliding friction μ	EN 13893	≥ 0,3
Dimensional variants after changes in relative humidity	EN 13329	length and width ≤ 0,9 mm
Straightness of the panels	EN 13329	≤ 0,30 mm / m
Height difference between elements	EN 13329	maximum ≤ 0,15 mm average ≤ 0,10 mm
Squared elements	EN 13329	≤ 0,2 mm / panel width
Flatness of the element width	EN 13329	concave ≤ 0,3 mm convex ≤ 0,4 mm
Flatness of the element length	EN 13329	concave ≤ 7 mm convex ≤ 14 mm
System pattern matching widthwise		+/- 2mm
Ship's planking matching widthwise		+/- 4mm

1)Information under www.floorsymbols.com